

AP20 Rec'd PCT/PTO 28 FEB 2006

1

CROSSLINKABLE HIGH PRESSURE POLYETHYLENE COMPOSITION, A
PROCESS FOR THE PREPARATION THEREOF, A PIPE AND A CABLE
PREPARED THEREOF

Field of the invention

The present invention relates to a crosslinkable high pressure polyethylene composition containing ethylene silane copolymer resin having a content of
5 silane of about 0.1 to 10 weight% and at least one silanol condensation catalyst. The invention further relates to a process for the preparation thereof, to a pipe made of said composition and to the use of the composition as an insulation for a cable.

10

Background of the invention

Presently commercially available ethylene-vinyltrimethoxysilane copolymer resins having a vinyltrimethoxysilane (VTMS) content in the range of about 1.0-2.0
15 weight% and a density below 925 kg/m³ are not suitable for pipe applications within the segment of plumbing and heating. Such water crosslinkable polyolefin pipes (PEX-b) do not have the properties required to pass the quality control point of hydrostatic pressure resistance at
20 95°C in accordance with i. e. the German medium density norm for PEX pipes, DIN 16894. The lifetime of a pipe according to this norm should be at least 1000 hour at 95°C, the circumferential stress in the pipe wall being 2.8 MPa. At a temperature as high as 95°C the hydrostatic
25 pressure resistance of the commercially available pipe above is very weak and such a pipe has a lifetime of less than 1 hour, i. e. the time to failure is less than 1 hour.

Attempts have been made in order to improve the
30 hydrostatic pressure resistance of pipes made of ethylene-vinyltrimethoxysilane copolymer resins by increasing

the density of the copolymer resin by mixing the resin with a high density polyethylene polymer (HDPE, i. e. PE made by low pressure polymerization). However, incorporating about 30 weight% high density polyethylene polymer into the resin and thereby increasing the density thereof to 934 kg/m³ does not result in an increased lifetime. Accordingly such pipes will not pass the quality control of DIN 16894.

Ethylene-vinylsilane copolymers, such as e. g. Visico™, may also be used for moisture crosslinking within the field of cable insulations. However, the prior art silane crosslinked polyethylene insulation materials have exhibited problems with so called "frozen layers", i. e. the molecules of the co-polymer will not have the time to relax when they hit the cold conductor and this will in turn lead to a thin layer of highly oriented molecules being formed close to the conductor. Such orientation of the molecules leads to deterioration of the mechanical properties. Previously, this problem has been solved by preheating the conductor or by decreasing the shear stresses by using a tube on die in stead of a pressure die. However, the investment in a preheater induces higher costs. Furthermore, a reduction of the die pressure by using a tube on die leads to a deterioration of the wetting properties, and this in turn involves reduced adhesion properties between the conductor and the insulation material.

Summary of the invention

The object of the present invention is to provide crosslinkable high pressure ethylene silane copolymer resins, wherein the above mentioned problems and drawbacks have been eliminated or at least alleviated.

For this purpose an ethylene silane copolymer resin is provided which has the benefits of being suitable for pipe applications within the segment of gas pipes, plumb-

ing and heating as well as for applications within the segment of cable insulations.

This object has been achieved by a crosslinkable high pressure polyethylene composition containing
5 ethylene silane copolymer resin having a content of silane of about 0.1 to 10 weight% and at least one silanol condensation catalyst, characterised in that the density of the composition is $>928 \text{ kg/m}^3$.

Preferred embodiments of the polyethylene composition are defined in dependent claims 2-10.
10

According to a preferred embodiment the density of the composition is $>933 \text{ kg/m}^3$.

According to another preferred embodiment the ethylene silane copolymer resin is an ethylene-vinyltriethoxysilane copolymer, an ethylene-gamma-methacryloxy-
15 triethoxysilane copolymer, an ethylene- vinyltrimethoxysilane copolymer or an ethylene-gamma-trimethoxysilane copolymer resin, preferably an ethylene- vinyltrimethoxysilane copolymer resin.

20 According to another preferred embodiment the ethylene-vinyltrimethoxysilane copolymer resin further comprises high density polyethylene (HDPE) in an amount of $<40 \text{ weight\%}$.

According to yet another preferred embodiment the
25 amount of high density polyethylene is 15-35 weight%, preferably 20-30 weight%.

Further, according to a preferred embodiment the MFR_2 at $190^\circ\text{C}/2.16 \text{ kg}$ is 0.1-100 g/10 min, more preferably 0.5-6 g/10 min and most preferably 1-4 g/10 min.


30 In another preferred embodiment of the invention the elongation at break is $>200\%$ as measured according to ISO 527 and the tensile strength at break is $>12.5 \text{ MPa}$ as measured according to ISO 527.

The gel content is preferably $>65 \text{ weight\%}$ as measured according to ASTM D 2765 and preferably the polyethylene composition further comprises 0.1-2.0 weight% of a
35 drying agent.

Another object of the present invention is to provide a method for the preparation a crosslinkable polymer composition according to any of claims 1-10.

This object has been achieved by a process for the
5 preparation a crosslinkable polymer composition according to any of claims 1-10, characterised in that the process is a high pressure process at a pressure above 1200 bar.

According to a preferred embodiment the polymer composition is crosslinked in the presence of a silanol condensation catalyst comprising a compound of formula (I):
10



or a precursor thereof, Ar being a hydrocarbyl substituted aromatic group comprising at least 14 carbon atoms.

15 In another embodiment of the invention the polymer composition is crosslinked in the presence of a silanol condensation catalyst preferably dibutyl-tin-dilaurate.

Another object of the present invention relates to a pipe made of a crosslinkable polymer composition according to any of claims 1-10.
20

In a preferred embodiment of the invention the pressure resistance at 95°C is at least 2.8 MPa, more preferably 3.6 MPa and most preferably 4.4 MPa for a failure time of at least more than 1000 hours.

25 Finally, the composition of the invention may advantageously also be used as an insulation for a cable.

By the invention a polymer composition is provided which has the properties required to pass the quality control point of hydrostatic pressure resistance at 95°C in accordance with i. e. the German high density norm for PEX pipes, DIN 16892. The lifetime of a pipe according to this norm should be at least 1000 hours at 95°C, the circumferential stress in the pipe wall being 4.4 MPa.
30

Accordingly, by the composition of the invention
35 higher pressure resistance is also achieved. Furthermore a high pressure reactor may be used for the production of the composition of the invention.


By the invention a polymer composition is provided which may be used as an insulation for an electrical cable fulfilling the mechanical demands outlined in e. g. VDE 0276-603 ("Verband Deutscher Elektrotechniker") without any requirement of preheating the conductor or any need for protection layers, e. g. polyester tapes, in order to avoid migration of plastisizer from the PVC jacket, commonly used in cables.

Other objects, features, advantages and preferred embodiments of the present invention will become apparent from the following detailed description when taken in conjunction with the appended claims.

Detailed description of preferred embodiments

It is well known to use additives to crosslink polymers since this improves most of the properties of the polymer such as heat resistance, chemical resistance and mechanical strength, etc. Crosslinking may be performed by condensation of silanol groups contained in the polymer which can be obtained by hydrolysis of silane groups. For the crosslinking of such polymers, a silanol condensation catalyst must be used. Conventional catalysts are for example tin-organic compounds such as dibutyl tin dilaurate (DBTDL). It is further known that the crosslinking process advantageously may be carried out in the presence of acidic silanol condensation catalysts, such as e. g. Ambicat™ from Borealis AB.

According to one embodiment of the invention the crosslinking process is carried out in the presence of a silanol condensation catalyst comprising a compound of formula (I):



or a precursor thereof, Ar being a hydrocarbyl substituted aromatic group comprising at least 14 carbon atoms. According to another preferred embodiment of the invention the polymer composition is crosslinked in the

presence of a silanol condensation catalyst, preferably dibutyl-tin-dilaurate.

By additionally admixing of <40 weight%, more preferably 15-35 weight% and most preferably 20-30 weight% of
5 a high density grafted silane PEX material to the two component blend allow to pass the quality control point at 95°C, the circumferential stress in the pipe wall being 4.4 MPa as stated in the German high density norm for PEX pipes, DIN 16892.

10 The present invention will now be illustrated by way of non-limiting examples of preferred embodiments in order to further facilitate the understanding of the invention.

15 Examples

Example 1

Tests were performed on pipes produced from different polymer compositions and the results are shown below in table 1.

20 The following polymers were used in the examples:

Polymer A: High pressure produced ethylene-vinyl trimethoxysilane copolymer having a density of 930.5 kg/m³, MFR_{2.16}=1.9 g/10 min and a VTMS content of 1.9 weight%. Produced in a tubular reactor at 2550 bar and
25 250°C.

Polymer B: High pressure produced ethylene-vinyl trimethoxysilane copolymer having a density of 925 kg/m³, MFR_{2.16}=0.9 g/10 min and a VTMS content of 1.25 weight%. Produced in a tubular reactor at 2400 bar and 280°C.

30 Polymer C: High pressure produced ethylene-vinyl trimethoxysilane copolymer having a density of 922 kg/m³, MFR_{2.16}=0.9 g/10 min and a VTMS content of 1.25 weight%. Produced in a tubular reactor at 2300 bar and 310°C.

Polymer D: High pressure produced ethylene-vinyl trimethoxysilane copolymer having a density of 922 kg/m³,
35 MFR_{2.16}=0.9 g/10 min and a VTMS content of 1.9 weight%. Produced in a tubular reactor at 2300 bar and 310°C.

Polymer M-1: High density polyethylene (i. e. low pressure polyethylene) having a density of 954 kg/m³ and MFR_{2.16}=4 g/10 min.

Polymer M-2: High density grafted silane PEX polymer
5 (i. e. silane grafted, cross-linked, low pressure polyethylene) having a density of 950 kg/m³ and MFR_{5.0}=1 g/10 min.

PVC-Jacket: typical PVC jacket formulation consisting of 20% plastisizer, e. g. dioctylphthalate, DOP, 20
10 weight% chalk and lead stabilizer.

Catalyst master batch CMB-1: In all examples 5% of CMB-1 was dry blended into the polymers prior to extrusion. CMB-1 consists of 1.7% dodecylbenzenesulphonic acid crosslinking catalyst, drying agent and antioxidants
15 mixed into an ethylene butylacrylate copolymer. Butylacrylate content: 17 weight%, MFR₂=4.5 g/10 min.

Catalyst master batch CMB-2 consists of a standard tin silanol condensation catalyst dibutyl-tin-dilaurate (1%) and antioxidants mixed into a high density polyethylene. In all pipe examples 5% of CMB-2 was dry blended
20 into the polymers prior to extrusion. The blend was extruded to 32x3 mm natural pipes which were kept in a water bath at 95°C for at least 16 hours. Each pipe was pressure tested according to DIN 16894/16892.

25 The tested cables were manufactured in the following way: Cables consisting of an 8 mm² compact aluminium conductor and an insulation thickness of 0.7 mm were produced in a Nokia-Maillefer 60 mm extruder at a line speed of 75 m/min.

30 Die: Pressure (wire guide 3.1 mm, die 4.4 mm).
Conductor temperature: 20°C (non-pre-heated conductor) or 110°C (pre-heated conductor).
Cooling bath temperature: 23°C.
Screws: Elise.

35 Temperature profile: 170-180-190-190-190-190-190-190°C.

5% of the crosslinking catalyst master batch CMB-1 was dry blended into the polymers prior to extrusion.

In order to measure the influence of plastisizer migration the cable core produced according to the description above was coated with a 2 mm PVC jacket. The Mechanical evaluation of the cables were performed according to ISO 527.

Table 1

Composition	VTMS weight%	MFR ₂ g/10 min	Density kg/m ³	Temp °C	Stress MPa	Failure time h
Quality control point, DIN 16874				95	2.8	>1000
Polymer D, LDPE VTMS copolymer	1.9	0.9	922	95	2.8	0.7
Blend of polymer D with 30 weight% Polymer M-1	1.4	1.2	934	95	2.8	0.7
Polymer A, MDPE VTMS co-polymer	1.9	1.9	930	95	2.8	>7700 no failure

10

From table 1 it is clearly shown that by increasing the density of the copolymer resin (polymer D) by blending with a high density polyethylene polymer (30 weight% polymer M-1) will not result in passing the quality control point of pressure resistance at 95°C, see table 1. By increasing the density of the ethylene-vinyltrimethoxysilane copolymer base resin to 930 kg/m³ (polymer A) the extruded and afterwards crosslinked pipes pass the quality control point of pressure resistance at 95°C as stated in the German medium density norm for MD-PEX pipes, DIN 16894.

15

20

Example 2

By blending high density polyethylene into the ethylene-vinyltrimethoxysilane copolymer (polymer A) the hydrostatic pressure resistance will be increased. In table 2 below, the hydrostatic pressure behaviour of the

25

medium density ethylene-vinyltrimethoxysilane copolymer (polymer A) and a blend of this silane copolymer with 15 weight% and 30 weight% high density polyethylene (polymer M-1) are shown. The gel content should preferably be >65% as measured according to ASTM D 2765.

Table 2

Composition	Density kg/m ³	Gel content % ASTM D 2765	Stress MPa	Failure time hours
Polymer A, 930 kg/m ³	930	85	3.2 3.0 2.8	1.3 89 and 17.2 >7700 no failure
+ 15 weight% HDPE	934	75	3.6 3.4 3.2	3.3 4.9 >6500 no failure
+ 30 weight% HDPE	937	68	3.8 3.6	12 and 3.7 545 and 628

Example 3

40 weight% of silane crosslinkable medium density polyethylene (MEPE) product polymer A having a density of 930 kg/m³ was blended with 30 weight% of grafted silane crosslinked PEX high density polyethylene product polymer M-2 with a density of 950 kg/m³ and 30 weight% of high density polyethylene product polymer M-1 having a density of 954 kg/m³. The pressure resistance in accordance with the quality control point of pressure resistance at 95°C as stated in the German high density norm for HD-PEX pipes., DIN 16892. The gel content should preferably be >65%, measured according to ASTM D 2765.

Table 3

Composition	Density kg/m ³	Gel content % ASTM D 2765	Temp °C	Stress MPa	Failure time hours
Quality control point DIN 16892		>65	95	4.4	>1000
Polymer A	930	85	95	4.4	0.1
Polymer A /M-1/M-2 (40/30/30 weight%)	943	68.5	95 95	4.4 4.6	>1400 290

Example 4

In order to investigate the need of preheating the conductor cables were produced with and without preheating of the conductors as described above. Some cable
 5 cores were coated with a 2 mm PVC jacket and aged in a heating oven at 100°C for 168 hours. The results are presented in table 4.

Table 4

Material	Specified demands (e. g. VDE 0273-603)	Polymer A +5% CMB-1	Polymer B +5% CMB-1	Polymer C +5% CMB-1
Density (kg/m ³) ASTM D 2839		930	925	922
Insulation extruded on non-preheated conductor				
Tensile strength at break (MPa) ISO 527	>12.5	15.0	13.1	12.5
Elongation at break (%) ISO 527	>200	245	204	180
Insulation extruded on preheated conductor				
Tensile strength at break (MPa) ISO 527	>12.5	24.7	21.9	19.7
Elongation at break (%) ISO 527	>200	440	368	361
Ageing of cable in contact with PVC jacket, 168h, 100°C				
Change of tensile strength at break (%)	<25	18	23	>30
Change of elongation at break (%)	<25	15	22	>30
Weight increase (%)	No requirement	12	15	19

The results presented in table 5 show that polymers A and B fulfil the specified requirements (e. g. VDE 0273-603) without any need of preheating or use of protection layers between the PVC jacket and the insulation.

CLAIMS

1. A crosslinkable high pressure polyethylene composition containing ethylene silane copolymer resin having
5 a content of silane of about 0.1 to 10 weight% and at least one silanol condensation catalyst, characterized in that the density of the composition is $>928 \text{ kg/m}^3$.

2. A crosslinkable high pressure polyethylene composition according to claim 1, wherein the density of the
10 composition is $>933 \text{ kg/m}^3$.

3. A crosslinkable high pressure polyethylene composition according to claim 2, wherein the ethylene silane copolymer resin is an ethylene-vinyltriethoxysilane copolymer, an ethylene-gamma-methacryloxytriethoxysilane
15 copolymer, an ethylene- vinyltrimethoxysilane copolymer or an ethylene-gamma-trimethoxysilane copolymer resin, preferably an ethylene- vinyltrimethoxysilane copolymer resin.

4. A crosslinkable high pressure polyethylene composition according to claim 3, wherein the ethylene- vinyl-
20 trimethoxysilane copolymer resin further comprises high density polyethylene in an amount of $<40 \text{ weight\%}$.

5. A crosslinkable high pressure polyethylene composition according to claim 4, wherein the amount of high
25 density polyethylene is 15-35 weight%, preferably 20-30 weight%.

6. A crosslinkable high pressure polyethylene composition according to any of claims 1-5, wherein the MFR₂ at
30 $190^\circ\text{C}/2.16 \text{ kg}$ is 0.1-100 g/10 min, more preferably 0.5-6 g/10 min and most preferably 1-4 g/10 min.

7. A crosslinkable high pressure polyethylene composition according to any of claims 1-6, wherein the elongation at break is $>200\%$ as measured according to ISO
35 527.

8. A crosslinkable high pressure polyethylene composition according to any of claims 1-7, wherein the ten-

sile strength at break is >12.5 MPa as measured according to ISO 527.

9. A crosslinkable high pressure polyethylene composition according to any of claims 1-8, wherein the gel
5 content is >65 weight% as measured according to ASTM D 2765.

10. A crosslinkable high pressure polyethylene composition according to any of claims 1-9, wherein the polyethylene composition further comprises 0.1-2.0
10 weight% of a drying agent.

11. A process for the preparation a crosslinkable polymer composition according to any of claims 1-10
c h a r a c t e r i s e d in that the process is a high pressure process at a pressure above 1200 bar.

15 12. A process according to claim 11, wherein the polymer composition is crosslinked in the presence of a silanol condensation catalyst comprising a compound of formula (I):

20 ArSO_3H (I)

or a precursor thereof, Ar being a hydrocarbyl substituted aromatic group comprising at least 14 carbon atoms.

25 13. A process according to claim 11, wherein the polymer composition is crosslinked in the presence of a silanol condensation catalyst, preferably dibutyl-tin-dilaurate.

30 14. A pipe made of a crosslinkable polymer composition according to any of claims 1-10.

15. A pipe according to claim 14, wherein the pressure resistance at 95°C is at least 2.8 MPa, more preferably 3.6 MPa and most preferably 4.4 MPa for a failure time of at least more than 1000 hours.

35 16. Use of a crosslinkable polymer composition according any of claims 1-10 as an insulation for a cable.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP2004/009630

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08J3/24 C08L43/04 H01B3/44 F16L9/12

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08J C08L H01B F16L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 492 760 A (SARMA HARIDOSS ET AL) 20 February 1996 (1996-02-20) column 1, lines 8-13 column 2, line 15 - column 8, line 32; claims; examples; tables -----	1-16
X	EP 0 501 340 A (QUANTUM CHEM CORP) 2 September 1992 (1992-09-02) page 2, lines 1-6 page 3, line 19 - page 6, line 36; claims; examples -----	1-16
X	US 5 430 091 A (MAHABIR CARL M) 4 July 1995 (1995-07-04) column 1, lines 7-30 column 2, line 15 - column 4, line 64 column 9, lines 11-49 claim 12; tables -----	1-16
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the International filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the International filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- *A* document member of the same patent family

Date of the actual completion of the International search	Date of mailing of the International search report
8 November 2004	19/11/2004
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Authorized officer Otegui Rebollo, J

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP2004/009630

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with Indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>US 4 117 195 A (MAILLEFER CHARLES ET AL) 26 September 1978 (1978-09-26) column 1, lines 4-22; claims; examples 16-18</p> <p style="text-align: center;">-----</p>	1-16

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP2004/009630

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5492760	A	20-02-1996	NONE	
EP 0501340	A	02-09-1992	AT 136571 T	15-04-1996
			CA 2061465 A1	26-08-1992
			DE 69209700 D1	15-05-1996
			EP 0501340 A2	02-09-1992
			JP 6041373 A	15-02-1994
			MX 9200784 A1	01-08-1992
			US 5312861 A	17-05-1994
			US 5266627 A	30-11-1993
US 5430091	A	04-07-1995	CA 2137218 A1	12-11-1995
US 4117195	A	26-09-1978	GB 1526398 A	27-09-1978
			AT 345554 B	25-09-1978
			AT 923275 A	15-01-1978
			AU 503860 B2	27-09-1979
			AU 8727975 A	09-06-1977
			BE 836338 A1	08-06-1976
			CA 1066010 A1	13-11-1979
			CH 634253 A5	31-01-1983
			CH 627402 A5	15-01-1982
			DE 2554525 A1	16-06-1976
			ES 443269 A1	16-04-1977
			FR 2293776 A1	02-07-1976
			IT 1056172 B	30-01-1982
			JP 51082361 A	19-07-1976
			JP 58025583 B	28-05-1983
			MY 15680 A	31-12-1980
			MY 15780 A	31-12-1980
			NL 7514222 A ,B,	09-06-1976
			NO 754113 A ,B,	09-06-1976
			SE 411765 B	04-02-1980
			SE 7513728 A	08-06-1976
			ZA 7507532 A	24-11-1976